

TECHNICAL DATA SHEET
ECOPROTETTIVO FERRO

Technical characteristics

ECOPROTETTIVO FERRO by OIKOS is a 100% acrylic, transparent, protective coating for metal. It is non-yellowing, scratch resistant, water repellent and washable, unalterable over time. Protecting the metal, the product brings out and highlights the beauty and the decorative patterns of the support, with a gloss effect. The product has a decorative function, not an anticorrosive one. It is ideal to protect ECOSMALTO FERROMICACEO by OIKOS from wear and dirt. The product has a low odour level, is non-inflammable and friendly to both humans and the environment.

Ideal use

Protection for ECOSMALTO FERROMICACEO by OIKOS

Surface preparation

Clean the surface to be treated, removing any dirt, dust and grease with the appropriate products

Application method

Apply one or two coats of ECOPROTETTIVO FERRO not diluted by brush or roller leaving 6 hours between coats. Dilute ECOPROTETTIVO FERRO 5 ÷ 10% with drinkable water for application by spray gun (0.8 ÷ 1.3 mm nozzle)

Technical characteristics: the application

Dilution	By brush or roller: ready to use. By spray gun 5 ÷ 10% drinkable water
Yield	12 ÷ 14m ² /l per coat according to the surface
Application tools	Brush, roller or spray gun (0.8 ÷ 1.3 mm nozzle)
Application temperature	+5°C ÷ +36°C (relative humidity not higher than 80%)
Drying time: tack free	1 ÷ 2 h (temperature= 20°C humidity not higher than 75%)
Drying time: fully cured	12 h (temperature= 20°C humidity not higher than 75%)
Tools cleaning	Water

Technical characteristics: the product



OIKOS S.P.A. a socio unico
Direzione e coordinamento OIKOS HOLDING S.P.A.
 Sede legale, amministrativa e produttiva
 Via Cherubini, 2 - 47043 Gatteo Mare (FC)
ITALIA - T +39 0547 681412 - F +39 0547 681430
INTERNATIONAL - T +39 0547 681460 - F +39 0547 681470
 CF e P.IVA e Reg. Imp. CCIAA FC n. 01970010409
 info@oikos-group.it - www.oikos-group.it

Composition	acrylic resins in water dispersion, additives to aid in application and the formation of the surface film.
Specific weight	1 kg/l +/-3%
PH	8 ÷ 9
Viscosity	600÷1200 +/-5% CPS Brookfield (RVT 20 revs/min at 25°C)
Storage temperature	+2°C ÷ +36°C. Keep from freezing
Fire reaction:	negative when the product is applied onto a non inflammable surface: water based material with dry thickness of less than 0.600 mm
Resistance to Abrasion	conforms to norm DIN 53 778: resistant to at least 5,000 abrasive cycles
Emission limits of Volatile Organic Compounds (VOC) according to directive 2004/42/CE	Classification: A/d; VOC: 55g/l (max); Limit Phase II (from 01/01/ 2010): 130g/l
Packaging	Litres 0,75 – 2.25

Safety Information

The product is free of heavy metals such as lead or chrome. It does not contain toxic solvents, aromatics or chlorides. There is no risk of any dangerous polymerisation. The product is considered to be a non-dangerous substance if used in the technically correct manner. Normal cautionary measures for the handling of water based paints are advised. No special arrangements are required for the storage, movement and transportation of the product; the containers, residue, eventual spilt material should be cleaned up using absorbent inert material such as sand, soil etc. etc. and then disposed of in accordance with the regional and national regulations in force at that time. Transportation must be carried out in accordance with international agreements.

Specifications

Clean the surface to be protected, removing any dirt, dust and grease with the appropriate products. Apply two coats of a protective coating for metal such as ECOPROTETTIVO FERRO by OIKOS. All must be carried out in accordance with the norms of application, at a cost ofmq. inclusive of materials and labour. Scaffolding not included

Note

The company Oikos Spa guarantees, to the best of its own technical and scientific knowledge, that the information contained in this technical data sheet is correct.

Notwithstanding that indicated above, Oikos takes no responsibility for the results obtained through the use of this product in as much as it is not possible for Oikos to check or control the application method used. For this reason, we recommend that you check carefully that each product chosen, is suitable for each individual use to which it is put.



OIKOS S.P.A. a socio unico
Direzione e coordinamento OIKOS HOLDING S.P.A.
 Sede legale, amministrativa e produttiva
 Via Cherubini, 2 - 47043 Gatteo Mare (FC)
 ITALIA - T +39 0547 681412 - F +39 0547 681430
 INTERNATIONAL - T +39 0547 681460 - F +39 0547 681470
 CF e P.IVA e Reg. Imp. CCIAA FC n. 01970010409
 info@oikos-group.it - www.oikos-group.it